

Quarry Location:
Wattscliffe Quarry,
Cliffe Lane, Elton,
Derbyshire, UK



Technical Results

Description	Medium Grained Sandstone Durable with good weathering qualities	
Country of Origin	UK	
Geological Type	Carboniferous / Millstone Grit	
Colour	Lilac / Grey	
Density	2230 kg/m ³	
Compressive Strength	56 MPa	BS EN 1926 (1999)
Water Absorption	4.75%	BS EN 13755
Porosity	17.20%	BS EN 1936 (1999)
Durability	Tests indicate that failure due to frost action is unlikely	BS EN 1341 (2001)
Saturation co-efficient	0.67%	BRE 89
Acid Immersion	Pass	BRE 141
Average Block Size	2000L x 1000W x 1000H	

Sales:
Block Stone Limited
Grant House
Prospect Way
Hutton
CM13 1XD

Tel: +44 (0) 1246 554450
Email: sales@blockstone.com

www.blockstone.com

Please note that stone is a natural product and all results are subject to variation